Rubiomonocoat SUNPRIMER COLOR (Duo systems)

DESCRIPTION:

Rubio Monocoat Sunprimer Color is a waterborne primer, with a spectacular penetration of the colour pigments through nanotechnology. It protects the wood against UV-discolouring and prevents the growth of fungi, moist, mildew and scaling. RMC Sunprimer Color needs to be applied as a pre-treatment in combination with RMC Decking Oil 2C or RMC Siding Oil.

RMC Sunprimer Color protects the wood from damage caused by photo-oxidation thanks to its strengthening effect on the lignin.

APPLICATION:

- 1. Apply only on raw, totally untreated wood. It is essential to remove completely all previous treatment products.
- 2. Clean the surface with RMC Exterior Wood Cleaner.
- 3. Apply RMC Sunprimer Color with a spray gun, brush, roller or cloth.
- 4. Allow to dry until the surface feels dry to the touch.
- 5. Apply RMC Decking Oil 2C or RMC Siding Oil.

Available in a wide range of wood tones and colours

CONSUMPTION:

The consumption of RMC Sunprimer Color varies according to the following parameters:

- 1. Wood density the softer the wood, the higher the consumption.
- 2. Humidity content the wood should be dry. Don't apply if the humidity content of the wood exceeds 12%.
- 3. Ambient temperature should be between 15°C and 27°C, with a relative humidity of less than 80%. Do not apply in full sun or at high temperatures.
- 4. Preparation the preparation method of the wood sandpapered, brushed or shaved - has an influence on the consumption

RMC Sunprimer Color

Consumption estimate - the wood needs to be fully saturated with RMC Sunprimer Color. Do not exceed the specified quantities.

Indicative consumption quantities:

RMC Sunprimer Color: New wood

1 l = +/- 20 - 35m2 Exotic and hard woods:

(+/- 30 - 50 g/m2)

Resinous and soft woods: 1 l = +/- 15 - 20m2

(+/- 50 - 60 g/m2)

DISCLAIMER: It is the responsibility of the user to determine through own testing whether the product is suited for its chosen application. Muylle Facon NV is not liable for any resultant damage. The above information may be subject to amendments, which will be published in revised versions of the technical sheet. We waive all responsibility for unsatisfactory results that are due to causes unrelated to the quality of the product. This technical information has been collected on the basis of current information and knowledge. The most recent technical sheets can be requested or are available on the website.







Consult the safety sheet before use. Date TDS: 10/06/11



MADE IN BELGIUM by N.V. MUYLLE - FACON S.A.

Ambachtenstraat 58 - B-8870 Izegem (Industriezone Abele) Tel. +32 (0)51 30 80 54 - Fax + 32 (0)51 30 99 78 - HRK 1823 info@muyllefacon.be - www.rubiomonocoat.com

RMC Sunprimer Color: Renovation, or after use of RMC Exterior Wood

All renovations shall be done in compliance with art and best practices and the Rubio Monocoat user instructions.

Exotic and hard woods: 1 l = +/- 15 - 25m2

(+/- 40 - 60 g/m2) 1 l = +/- 10 - 15m2 Resinous and soft woods:

(+/- 60 - 100g/m2)

These usages are merely indicative. Results depend on wood type and method of preparation. It is always recommended to make a sample in order to calculate the exact usage.

TECHNICAL SPECIFICATIONS:

Liquid

Low viscous (< 50 mPa.s at 15°C, Brookfield RVT)

pH: 6 - 8 (20°C) Odour: specific Density: 1,025 kg/l

STORAGE:

The product can be stored for up to 12 months. Store in dry conditions and in the original packaging. Do not allow to freeze.

PACKAGING:

0,5 - 1 - 5 - 10 - 25 liter.

